

Carbon fabric 400g twill

		Tolerance	Standard
Weight	400g/m ²	± 5%	ISO 4605
Binding	Body 2x2		ISO 2113
Width	1.20m	± 2.5%	ISO 22198
Chain	5,0 Fd/cm (FT300B 6K 400 tex)		ISO 4602
Shot	5,0 Fd/cm (FT300B 6K 400 tex)		ISO 4602
Thickness	0.40mm	± 2.5%	ISO 5084(**)
Weight distribution	Warp 50% / Weft 50%		
Fiber	TORAY 6K FT300B		
Mechanical Features	Tensile strength 3530MPa Elasticity 230GPa		

(**) Theoretical thickness for an epoxy laminate with 40% of the reinforcement in volume.

The information contained in this publication is based on careful research. They serve to provide information, but do not exempt the user from independent experiments for the intended purposes and from examinations of the risk of infringement of any intellectual property rights of third parties. The information is non-binding and, in particular, does not represent warranted properties within the meaning of laws. Liability for the accuracy and completeness of the information is excluded.