

Epox R2 + Härter H2 middle

Technical Data Sheet Epox R2 + Härter H2 middle

Characteristics

Solvent-free two-component epoxy resin system free of alkylphenols and benzyl alcohol

Application and properties

The epoxy system Epox R2 + hardener H2 middle is a solvent-free 2-component EP binder that is particularly suitable for thick-layer casting applications (up to 5cm) with high transparency due to its low exothermia and tendency to yellowing. Despite the long pot life, it offers good mechanical properties.

Specification Comp. A

Feature	Value	Unit	Measurement Method
Viscosity at 25 °C	500 ± 70	mPas	ISO 3219
FTIR Comparison	PASS		
EP equivalent weight	200 ± 10	g/Eq.	
Refractive index	1.544 ± 0.001		ASTM D 1747
Density at 23°C	1,08-1,12	g/cm ³	ISO 2811-2

Specification Comp. B

FTIR Comparison	PASS		
Hazen Color Number	<50	mgPt/L	DIN EN ISO 6271
Amine number	355 ± 15	mgKOH/g	
Refractive index	1.461 ± 0.001		ASTM D 1747
Density at 23°C	0,96-1,00	g/cm ³	ISO 2811-2

System Features

Mixing ratio	100/40	Wt Parts	Resin/Hardener
Initial viscosity at 25 °C	approx. 300	mPas	ISO 3219
Pot life*	> 7	h	v. 23 -> 40°C with 500ml
min. Curing temperature	16	°C	
Shore D n. 7 d RT	84		DIN ISO 7619-1

Storage

At room temperature, the shelf life of both components in originally packaged containers is at least 12 months.

Information on occupational health and safety

When processing epoxy resins and hardeners, the usual precautions for handling chemicals as well as applicable official occupational health and safety regulations and environmental protection regulations must be observed. Particular attention must be paid to skin protection and the selection of suitable protective gloves. Detailed information on hazards, labelling, occupational health and safety and environmental protection can be found in the product safety data sheet.

*The gel time is approximately twice the stated value

The information contained in this publication is based on careful research. They serve to provide information, but do not exempt the user from independent experiments for the intended purposes and from examinations of the risk of infringement of any intellectual property rights of third parties. The information is non-binding and, in particular, does not represent warranted properties within the meaning of laws. Liability for the accuracy and completeness of the information is excluded.

As of 07/2026