

Technical Data Sheet

Textile Glass Cut Fiberglass Chips

DESCRIPTION

Fiberglass chips – cut E-fiberglass strands, suitable for wet gypsum applications, for BMC, SMC and DMC, as well as for mixing with PP, PA, PET, but can also be used for many general applications.

Also suitable for the production of fibre-reinforced fillers and adhesive compounds, as well as coupling layers in mould making.

- Excellent mechanical properties
- Good impregnation properties
- For polyester and epoxy resins
- Made by crushing E-glass

TECHNICAL FEATURES

Glass Type:	E-glass direct roving	Moisture content:	<2.0%
Softening point:	840°C	Polyester Fadenge content:	0%
Filament diameter:	17m +/-4	Fiber Length:	4.6 or 12mm
Loss of Ignition:	<2.0%	Fiber Length Tolerance:	+/-1mm

STORAGE

It is recommended to store the fiberglass products in a cool and dry environment. The recommended temperature range of storage is 10°C - max. 30° and a relative humidity between 50 - 75%.

The fiberglass products should remain in the packaging until shortly before use.

The information contained in this publication is based on careful research. They serve to provide information, but do not exempt the user from independent experiments for the intended purposes and from examinations of the risk of infringement of any intellectual property rights of third parties. The information is non-binding and, in particular, does not represent warranted properties within the meaning of laws. Liability for the accuracy and completeness of the information is excluded.
