






# Technical Data Sheet - Product Information

## Product: UNIPOL


**Characteristics:**

2c universal polyester filler with a wide range of application. Typically used as a stopper or as fine-putty. Little afterbake and easy to sand. Due to its high thixotropic quality airo UNIPOL can be applied to vertical surfaces. Excellent adhesion on various bases especially zinc-galvanised sheets, hot dip galvanised sheets, sheet steel, aluminium, wood and glass-fibre reinforced body parts based on polyester material.

**Range of application:**

Car-refinishing, industry

**Chemical basis:**

UNIPOL: Unsaturated polyester resins, inert filling material, thixotropic agents and pigments.

Hardener: Benzoyl peroxide

**Instructions for use:**

Clean surface from dirt and grease. Remove rust and lacquer coat. Rough up surface with abrasive paper or sand blast. Mix the required quantity of airo UNIPOL with approx. 2% hardener paste and apply within a period of 4-6 minutes.

**Do not use** on wash-primers and other acid-curing substrates.

**Pot life:**

With 2% hardener: 4-6 minutes

Excess of hardener does not accelerate the polymerisation rate but might cause loss of adhesion and/or discoloration of the following paint films.

**Mixture:**

100 parts: airo UNIPOL  
2 parts: Hardener

**Temperature conditions:**

Material and surrounding temperature should range between +18 °C and +25 °C. Do not apply at temperatures below +5 °C

**Disposal:**

Disposal according to local regulations.

**Sanding:**

Paper P 80 – 280

Please dry sand as polyester materials are susceptible to water

**Storage stability:**

24 months in tightly closed tins when kept at +20 °C.