


Technical Data Sheet - Product Information

Product: **FASERPLAST**



Characteristics:

2c polyester filler with glass fibres
Ideal for refinishing rusted body parts.
Excellent adhesion on various bases especially on sheet steel and glass-fibre reinforced body parts based on polyester material.




Range of application:

Car-refinishing, boat repair
Boat repair above the waterline.



Chemical basis:

FASERPLAST: Unsaturated polyester resins, coupler to improve sanding and adhesion properties, thixotropic agents and glass fibres
Hardener: Benzoyl peroxide




Instructions for use:

Clean surface from dirt and grease. Remove rust and old lacquer.
Rough up surface with abrasive paper or sand blast.
Mix the required quantity of airo FASERPLAST with approx. 2% hardener.
Apply within a period of 4-6 minutes.
Do not use on wash-primers, prime coats based on synthetic resins or nitro-cellulose undercoats.




Pot life:

With 2% hardener: 4-6 minutes
Excess of hardener does not accelerate the polymerisation rate but might cause loss of adhesion and/or discoloration of the following paint films.



Mixture:

100 parts: airo FASERPLAST
2 parts: weight Hardener




Temperature conditions:

Material and surrounding temperature should range between +18 °C and +25 °C.
Do not apply at temperatures below +5 °C

Disposal consideration:

Disposal according to local regulations.



Sanding:

Paper P 80 – 280
Please dry sand as polyester materials are sensitive to water.

Storage stability:

12 months in tightly closed tins when kept at +20 °C.